

					Mechanical Properties)			Chemical Composition								
Steel Quality	Surface type	Surface quality	Surface protection	Coating weight	Re	Rm	A (%)	C	Mn	P	S	Si	Al	Ti	Nb	V
DX51D+Z	BR	A	CO	Z100	317	374	32,1	0,04	0,28	0,014	0,017	0,017	0,041	0,001	0,002	0,001